

Kemgrout LD

High Performance Non-Shrink	Cementitious Grout
-----------------------------	--------------------

n Performance Non-Shrink Ce	mentitious Grout	
	A pourable cement base, non-shrink, hydraulic o	compound specially formulated for
	heavy-duty support under machine base plates,	cranes, railsetc
	The material is a blend of Portland cement, pre-	graded fillers, and additives which
Description	impart controlled expansion in the plastic state	whilst minimizing water demand. The
	low water requirements ensure high early streng	gth and long-term durability. The filler
	grading is designed to aid uniform mixing and m	inimize. segregation and bleeding
	Standards: Complies with ASTM C1107 Grade A,	ASTM C827, and CRD – C621
	Thickness: min.10 mm/ max. 75 mm	
Where to use	Kemgrout LD is used for general-purpose grouting over a wide range of applications, including heavy-duty support under machine base plates, cranes, rails, and stanchion bases. Also performed as anchoring for masts, anchor bolts etc.	
	• It adheres to concrete, mortars, stones steel &	iron.
	 It may be pumped, injected, vibrated, or compa 	acted.
A al	 Ready to use pre-packed material that eliminat 	es the possibility of site batching variations.
Advantages	 No metallic filler used which causes staining or deterioration due to rust expansion. 	
	Rapid gain of strength facilitating rapid installat	, .
	 Excellent mechanical properties and low perme the grout. 	eability ensure the long-term performance o
Properties		
Flexural strength: BS 4551,	1990 (For flowable consistency at 20 °C), ASTM C 348-	95
Age (days)	Flowable	
7	4 - 5 N/mm²	
28	10 - 11.0 N/mm²	
Setting Time At 20 °C		
Liquid Mortar	Initial 7.45 hrs	Final 9 hrs
Elastic Mortar	Initial 90 min	Final 180 min
Compressive strength		
Age (days):	Flowable	Trowable
1	18 N/mm²	20 N/mm ²
7	30 N/mm²	35 N/mm ²
28	35 - 40 N/mm²	45 N/mm ²

 $\label{eq:limited} \textbf{Ultimate anchorage bond strength}: 40 \ \text{N/mm}^2 \ \text{for concrete after 24 hrs.}$

Coefficient of thermal expansion: 11X10-6 $^{\circ}\text{C}.$

Thermal conductivity: 1.5 w/m $^{\circ}\text{C}$

Density: 2.1 Kg/lit

Expansion properties: An expansion of 1 - 4%. Compensates for plastic settlement in the unset material.



Product Data Sheet Edition 12.2022 Identification No. G A - 13 Kemgrout LD 1/3



Kemgrout HD 2/3

Surface Preparation	 Concrete surface: Must be free from oil. Grease, or any loosely adhering material. If the concrete surface is defective or has laitance, it must be cut back to a sound base. Bolt holes or fixing pockets must be blown clean of any dirt debris. Steel base plate: All rust traces must be removed either by mechanical means (e.g. abrasives) or by a suitable rust remover. The undersides and edges of the steel plate should then be cleaned from oil and dirt then protected with Kemkleen to prevent rust formation and ensure bonding with the Kemgrout LD. Expansion Joints: Shall be installed in accordance with local building codes. Never bridge an expansion, contraction, or construction joint.
	The quantity of water required to achieve the desired consistency and volume used should be in accordance with the following:
	• Flowable grout 3 – 3.25 lit/25 Kg Sack
Mixing	• Trowable grout 2.75 – 3 lit/25 Kg. Sack.
IAIIVIIIR	• For best results, a mechanically powered grout mixer should be used.
	• The selected water content should be accurately measured in the mixer.
	• Slowly add the total contents of the Kemgrout LD sack add and mix continuously for 5 min.
	ensuring homogeneous consistency.
Application	 Saturate the concrete surfaces with clean water prior to applying Kemgrout LD. Ensure that no free-standing water is present on the surfaces of foundations or in bolt holes. Place the grout within 20 min. of mixing to gain the benefit of the expansion process. Kemgrout LD may be placed in thickness up to 100 mm. in a single pour when used as an under plate grout. For thicker sections it is necessary to fill out Kemgrout LD with well-graded silt-free aggregates to minimize temperature rise. High points must be adequately vented to allow entrapped air to escape. Pouring should be from one side of the void to eliminate the entrapment of air or surplus pre-soaking water. The grout head must be maintained at all times so that a continuous grout front is achieved. Where large volumes have to be placed Kemgrout LD may be pumped. A heavy-duty diaphragm pump is recommended for this purpose. Screw feed and piston pumps are also suitable.
Specific Application	Grouting under base plates: Use flowable consistency. Grouting anchor bolts: Use trowable consistency. Grouting large volumes: For sections thicker than 100 mm. It is necessary to fill the Kemgrout LD with graded 10 mm. silt-free aggregate to minimize temperature. • The quantity of aggregate should not exceed 1-part aggregate to one part Kemgrout LD by weight. For such mixes, a conventional concrete mixer and pump should be used. • Unrestrained areas of a width exceeding 50mm should be trowelled after two hours from mixing.
Theoretical coverage	$2 \text{ kg/ m}^2 / 1 \text{mm thick}.$
Packaging	Kemgrout LD is supplied in 25 kg sacks.
Shelf life & Storage	Kemgrout LD has a shelf life of 12 months if kept in sealed bags in dry places.
Cleaning	Kemgrout LD should be removed from tools and equipment immediately after use with clean water .
Curing	On completion of the grouting operation, exposed areas that are not to be cut back should be thoroughly cured by means of water application, Kemcure , or wet hessian



Product Data Sheet Edition 12.2022 Identification No. G A - 5



 Kemgrout HD is non-toxic if comes in contact with skin.
 Use gloves to avoid contact with skins.
 If skin comes in contact, wash immediately with soap and water.
 Eye contamination must be immediately washed with water.
Do not breathe dust, Use a practical mask .
PROKEM provides the construction industry with a comprehensive range of construction
chemicals and specialty products answering the queries of modern engineers for trouble
free durable structure.
PROKEM designs tailor made products should there be critical application that requires
specific properties rather than our main range. For our customer's satisfaction.
PROKEM reserves the right to change the properties of its products.
All orders are accepted subject to our current term of sale & delivery.
Users must always refer to the most recent issue of the local product data sheet for the
product concerned, copies of which will be supplied on request.
PROKEM extends technical services to include after-sales support to assist users in the
proper handling of our products.



Product Data Sheet Edition 12.2022 Identification No. G A - 5 Kemgrout HD 3/3