

Kemgrout HD/F

High Performance Expanding Non-Shrink, Fiber Reinforced Cementitious Grout

Description	A pourable cement base, non-shrink, hydraulic compound specially formulated for heavy-duty support under machine base plates, cranes, rails ...etc	
	The material is a blend of Portland cement, pre-graded fillers, fibers, and additives which impart controlled expansion in the plastic state whilst minimizing water demand. The low water requirements ensure high early strength and long-term durability. The filler grading is designed to aid uniform mixing and minimize segregation and bleeding.	
	Fibers reduce shrinkage, increase strength energy absorption, and reduce spalling at a high temp. and increase fire resistance. Standards: Complies with ASTM C1107 Grade B or C and CRD-C621	
	Thickness: min.10 mm/ max. 75 mm	
Where to use	Kemgrout HD/F is used for general-purpose grouting over a wide range of applications, including heavy-duty support under machine base plates, cranes, rails, and stanchion bases. Also performed as anchoring for masts, anchor bolts... etc.	
Advantages	<ul style="list-style-type: none">• It has a unique 2-stages shrinkage compensating system, with an excellent water reducing action.• Ready to use pre-packed material that eliminates the possibility of site batching variations.• No metallic filler used which causes staining or deterioration due to rust expansion.• Rapid gain of strength facilitating rapid installation and early operation of the plant.• Excellent mechanical properties and low permeability ensure the long-term performance of the grout.	
Properties		
Flexural strength: ASTM348-95		
Age (days)	Flowable	
7	13 -14 N/mm ²	
28	35 - 40 N/mm ²	
Setting Time @ 20 °C		
Liquid Mortar	Initial 5 hrs	Final 8 hrs
Elastic Mortar	Initial 90 min	Final 180 min
Compressive strength ASTM C -109		
Age (days)	Flowable	Trowable
3	25 N/mm ²	31 N/mm ²
7	42 N/mm ²	42 N/mm ²
28	60 N/mm ²	66 N/mm ²
Bond strength to concrete (ASTM C 321)	1.2 N/mm ² (7 days)	
Ultimate anchorage bond strength	40 N/mm ² for concrete after 24 hrs.	
Coefficient of thermal expansion	11X10 ⁻⁶ °C	
Thermal conductivity	1.5 w/m °C	
Density	2.0 Kg/lit	
Expansion properties	An expansion of 1 - 4 %. Compensates for plastic settlement in the unset material	

Application	<ul style="list-style-type: none"> • Saturate the concrete surfaces with clean water prior to applying Kemgrout HD/F. • Ensure that no free standing water is present on surfaces of foundations or in bolt holes. • Place the grout within 20 min. of mixing to gain benefit of the expansion process. • Kemgrout HD/F may be placed in thickness up to 100 mm. in a single pour when used as an under plate grout. • For thicker sections it is necessary to fill out Kemgrout HD/F with well graded silt-free aggregates to minimize temperature rise. • High points must be adequately vented to allow entrapped air to escape. • Pouring should be from one side of the void to eliminate the entrapment of air or surplus pre-soaking water. • The grout head must be maintained at all times, so that a continuous grout front is achieved. • Where large volumes have to be placed Kemgrout HD/F may be pumped. A heavy duty diaphragm pump is recommended for this purpose. Screw feed and piston pumps are also suitable.
Specific application	<ul style="list-style-type: none"> • Grouting under base plates: Use flowable consistency. • Grouting anchor bolts: Use trowable consistency. • Grouting large volumes: For sections thicker than 100 mm. It is necessary to fill the Kemgrout HD/F with graded 10 mm. silt-free aggregate to minimize temperature. • The quantity of aggregate should not exceed 1-part aggregate to one part Kemgrout HD/F by weight. For such mixes a conventional concrete mixer and pump should be used. • Unrestrained areas of width exceeding 50mm should be trowelled after two hours from mixing.
Theoretical coverage	2 Kg/ m ² / 1mm thick.
Packaging	Kemgrout HD/F is supplied in 25 kg sacks.
Shelf life & Storage	Kemgrout HD/F has a shelf life of 12 months if kept in sealed bags in dry place.
Curing	On completion of the grouting operation, exposed areas which are not to be cut back should be thoroughly cured by means of water application , Kemcure or wet hessian.
Cleaning	Kemgrout HD/F should be removed from tools and equipment immediately after use with clean water .
Health and Safety	<ul style="list-style-type: none"> • Kemgrout HD/F is non-toxic if comes in contact with skin. • Use gloves to avoid contact with skins. • If skin comes in contact, wash immediately with soap and water. • Eye contamination must be immediately washed with water. • Do not breath dust, Use a practical mask.
Additional Information	<p>PROKEM provides the construction industry with a comprehensive range of construction chemicals and specialty products answering the queries of modern engineers for trouble free durable structure.</p> <p>PROKEM designs tailor made products should there be critical application that requires specific properties rather than our main range. For our customer's satisfaction.</p> <p>PROKEM reserves the right to change the properties of its products.</p> <p>All orders are accepted subject to our current term of sale & delivery.</p> <p>Users must always refer to the most recent issue of the local product data sheet for the product concerned, copies of which will be supplied on request.</p> <p>PROKEM extends technical services to include after-sales support to assist users in the proper handling of our products.</p>