

Kemflow Super G16

High Range Water-Reducing and Set Retarding Concrete Admixture

Description	<p>Kemflow Super G16 is a highly effective super plasticizer with a set-retarding effect for producing free-flowing concrete in hot climates. It is a substantial water reducing agent for promoting high early and ultimate strength, also it significantly improves the workability of concrete without increasing water demand.</p> <p>Standards: Complies with A.S.T.M. C-494 Type G.</p>
Where to use	<p>Kemflow Super G16 is used wherever high-quality concrete is required under difficult placing and climatic conditions. Kemflow Super G16 is used as a superplasticizer to:</p> <ul style="list-style-type: none"> • Reduce concrete permeability. • Long transport conditions • Eliminates plastic shrinkage cracking, and segregation. • increases high early strength, surface hardness and density. • Ready - mixed concrete. • Production of flowing concrete. • Pumped concrete.
Advantages	<ul style="list-style-type: none"> • Kemflow Super G16 provides the following advantages: • Especially suitable for hot climate, no excessive air-entrainment. • No adverse effect on ultimate strengths. • Increased water tightness. • Long-lasting control of slump loss. • Production of flowing concrete. • Up to 20% water reduction • Improved surface finish. • Substantial improvement in workability without increased water or the risk of segregation.
Properties	
Type	Synthetic dispersion
Nitrate content	Nil
Color	Brown
Specific gravity @ 23 °C	1.16 ±0.01
Chloride content	Nil to BS. 5075.
Dispensing	<p>The correct quantity of admixture should be measured by means of a recommended dispenser. The admixture should then be added to the concrete with the mixing water to obtain the best results.</p>
Direction for use	<p>Kemflow Super G16 should be added to the gauged water, but never to the dry aggregate or cement. Reduction of water is higher if the admixture is added to the concrete after 60 - 75% of the mixing water has been added.</p>
CURING	<p>PROKEM recommends the concrete be cured for 24 hours after finishing operations are complete by using Kemcure curing compound. spray applied surface contact curing membranes should be used in all cases.</p>

Job site mixing	Add the Kemflow Super G16 Concrete admixture to the concrete truck and let drum rotate for 7 minutes before discharge.
Compatibility	Other admixtures may be used in the same concrete batch with Kemflow Super G16 provided that such admixtures are added separately and the combination has no deleterious effect on the concrete.
Cleaning	Spillage of Kemflow Super G16 can be removed with water.
Theoretical Dosage Rate	0.8 – 3% by weight of cement. Exact dosage rates are dependent on the type of effect sought, quality of cement and aggregates, water/cement ratio and ambient temperature. Therefore, it is advisable to carry out trial mixes. Kemflow Super G16 is compatible with all types of Portland Cement including S.R.C...
Overdosing	an over dosage of Kemflow Super G16 will result in an increase in retardation as compared to that normally at the intended dosage The effects of overdosing will be further increased if sulphate resisting cement or cement replacement materials are used. however, no excessive amounts of air will be entrained.
Packaging	Available in: 25 Kg Pails 220 Kg Drums. 1000 Kg Tanks
Shelf life & Storage	Up to one year when stored in original unopened packaging out of direct sunlight and kept under cover protected from extremes temperature
Health and Safety	<ul style="list-style-type: none"> • Kemflow Super G16 is non-toxic. • Use gloves to avoid contact with skin. • If skin comes in contact, wash immediately with soap and water. • Do not use solvents. • Eye contamination must be immediately washed with water, then seek medical treatment.
Additional Information	<p>PROKEM provides the construction industry with a comprehensive range of construction chemicals and specialty products answering the queries of modern engineers for trouble free durable structure.</p> <p>PROKEM designs tailor made products should there be critical application that requires specific properties rather than our main range. For our customer's satisfaction.</p> <p>PROKEM reserves the right to change the properties of its products.</p> <p>All orders are accepted subject to our current term of sale & delivery.</p> <p>Users must always refer to the most recent issue of the local product data sheet for the product concerned, copies of which will be supplied on request.</p> <p>PROKEM extends technical services to include after sales support to assist users in a proper handling of our products.</p> <p>Environmental Considerations:</p> <p>Kemflow Super G16 Admixture is environmentally safe and contains no volatile organic compounds (VOCs).</p> <p>Kemflow Super G16 Admixture contains an anti-microbial biocide to inhibit mold and bacteria growth.</p>